

DESCRIPTION

PENEPOX™ SF PRIMER is a liquid form, rigid, two component, self-leveling, epoxy solvent-free primer with high impact and abrasion strength and very good resistance against acidic and basic solutions, common chemicals and detergents. PENEPOX™ SF PRIMER cures by reaction (cross linking) of the two components.

RECOMMENDED FOR

PENEPOX™ SF PRIMER is mainly used as a primer for polyurethane coatings, before the application of PENEPOX™ SF ELASTIC and epoxy systems and paints PENEPOX™.

- ▶ Concrete
- ▶ Terrazzo
- ▶ Troweled industrial floor
- ▶ Quarry tiles
- ▶ Power floated concrete
- ▶ Asphalt
- ▶ Wood.
- ▶ Metal, etc.
- ▶ Resin for the production of durable resin mortars of coloured quartz sand on decorative floors
- ▶ Stabilizing loose surface pieces of internal spaces

ADVANTAGES

- ▶ Solvent free
- ▶ Easy to apply
- ▶ Excellent anchoring to the surface
- ▶ Provides high tensile and impact strength
- ▶ Heat and frost resistant
- ▶ Provides strong resistance to chemicals and detergents
- ▶ Provides strong vapor barrier properties

TECHNICAL CHARACTERISTICS

Characteristics	Test Result	Test Method
Composition	Pigmented Epoxy resin + Hardener	
Color	Clean	
Mixing ratio	A : B = 100 : 50 (by mass)	
Hardness (Shore D Scale)	40	ASTM D 2240
Solids content	100%	Inside Lab Test
Adhesion to Concrete	> 3,7 N/mm ² (concrete failure)	EN 1542
Application temperature	12 °C to 35 °C (53 °F to 95 °F)	Conditions: 20 °C (68 °F), 50% RH
Workability time	40 min	
Tack free time	3-5 hours	
Light trafficking	12-24 hours	
Repaint time	12-18 hours	
Final curing time	7 days	

All data are average values obtained under laboratory conditions. Impractical use, temperature, humidity and absorption of the substrate may influence the above given values.

DIRECTIONS FOR USE

Surface Preparation: The surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the coating. Maximum moisture content should not exceed 5%. New concrete structures need to dry for at least 28 days. Old coatings, dirt, fats, oils, organic substances and dust need to be removed by a grinding

machine. Possible surface irregularities need to be smoothened. Any loose surface pieces and grinding dust need to be thoroughly removed.

NOTE: Careful surface preparation is essential for optimum finish and durability. The surface needs to be grinded with a stone- or a diamond-grinding machine. Do not wash surface with water.

Mixing: Pour the content of PENEPOX™ SF PRIMER B into the PENEPOX™ SF PRIMER A container and mix thoroughly for at least 3-4 mins, until the mixture becomes fully homogeneous. The mixing of the components has to be effected very thoroughly, especially on the walls and bottom of the pail, with a drilling mixer and a mixing wand.

Application: Apply the PENEPOX™ SF PRIMER A+B mixture by roller or brush, until the surface to be primed, is covered. If the area is to be coated with polyurethane sealant or coating, disperse 0,5-1 Kg/m² (0,1-0,2 lb/ft²) of dry quartz sand mix onto the primer, before it gets dry, and then let it dry.

After 12 – but not later than 18 hours – apply the next layer of polyurethane coating PENEPOX™ SF ELASTIC or epoxy coating PENEPOX™ CS.

NOTE: Keeping the timeline is very important to ensure the best bonding between layers.

Coverage: As a primer, 250 gr/m² (0,05 lb/ft²), in one layer.

SPECIAL CONSIDERATIONS

For the best results, the ambient and ground temperature during application and curing should be between 12 °C to 35 °C (53 °F to 95 °F). Low temperatures cause curing retardation, while high temperature speed up curing. High humidity may affect the final finish.

Careful compliance with the time margins is essential for an excellent result.

Contact PENETRON ROMANIA for further information regarding your project.

PACKAGING

PENEPOX™ SF PRIMER A+B is available in 4+2 kg (8,8+4,4 lb) and 8+4 kg (17,6+8,8 lb) containers.

STORAGE / SHELF LIFE

PENEPOX™ SF PRIMER can be stored for 12 months in its original packing (unopened container) at 5 °C – 35 °C (41 °F – 95 °F) in a cool, dry place. Keep away from wet areas and direct sunlight.

SAFE HANDLING INFORMATION

Avoid skin and eye contact. If contact is made, flush areas with lots of water and seek medical advice. Protective gloves, mask and goggles should be worn. For further information please refer to Safety Data Sheet. PENETRON

HELLAS S.A. has recently updated Safety Data Sheet on the safe use of PENETRON® products. Each Safety Data Sheet contains health and safety information for the protection of your employees and your customers. KEEP OUT OF REACH OF CHILDREN.

WARRANTY - DISCLAIMER

BEST IMPORT PRODUCTS PENETRON. warrants that the products manufactured by it shall be free from material defects and will conform to formulation standards and contain all components in their proper proportion. Should any of the products be proven defective, the liability to BEST IMPORT PRODUCTS PENETRON. shall be limited to replacement of the material proven to be defective, and BEST IMPORT PRODUCTS PENETRON shall in no case be liable otherwise or for incidental or consequential damage. BEST IMPORT PRODUCTS PENETRON MAKES NO WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AND THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES EXPRESSED OR IMPLIED. User shall determine the suitability of the product for its intended use and assume all risks and liability in connection therewith. BEST IMPORT PRODUCTS PENETRON may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information.